Kentucky Method 64-109-0<u>56</u> Revised <u>10/6/06</u> Supersedes 64-109-05 Dated 1/05/05

QUALIFICATION OF STEEL REINFORCEMENT TACK WELDERS

1. SCOPE: This method, based on modifications of the AWS (American Welding Society) Bridge Welding Code A5.1, A5.5, A5.18, or D1.4, current edition, outlines the procedures for qualifying tack welders for welding steel reinforcement. Information herein is taken from Section 605 of the Standard Specifications For Road and Bridge Construction.

2. PROCEDURE:

- 2.1. Use the bar stock and welding equipment that is required for fabrication of the steel at the precast or prestress producer's facility. Acceptable electrodes and welding processes are listed in Section 3.
- 2.2. Prepare 2 3 sample tack welds of the following 4 combinations: #3 4 (10 13 mm) to #6T (19T mm), #6 (19 mm) to #3 4T (10 13T mm), #4 (13 mm) epoxy to #5T (16T mm), and #5 (16 mm) epoxy to #4T (13T mm) where T is the short bar of the welded intersection. Samples do not necessarily need to be cut from a cage but the long bar should be in the vertical position when tack welded, thereby simulating actual welding conditions.
- 2.3. The bar to be tested shall be approximately 24 inches long. The 'T' cross bar shall be 6-8 inches long. The weld shall join the bars at $\frac{\text{mid point } +1}{\text{length}}$ of each $\frac{\text{long}}{\text{long}}$ bar.
- 2.4. Prepare the <u>bars samples</u> in the presence of the KYTC inspector. Securely tape <u>the 3 bars of each combination sample pairs</u> together. The inspector will deliver <u>the</u> test <u>bars samples</u> (and the appropriate forms) to the Division of Materials <u>Laboratory</u> for evaluation.
- 2.5. The Division of Materials' Physical Section will evaluate each <u>bar to determine if the</u> physical properties of the bar have been degraded by the weld <u>sample for tensile strength</u> across the point of the tack weld. Each <u>bar sample</u> must meet the minimum requirements for TENSILE and YIELD strength of the bar stock <u>as well as % ELONGATION and BEND. If any bar fails, the 3 bar combination fails. If any combination fails, the welder fails to qualify.</u>

3. ELECTRODES:

- 3.1. Shielded Metal-arc Process: Use only electrodes with low hydrogen classifications E7015, E7016, E7018, E7028, E9015, E9016, E9018, or E9028 according to AWS A5.1 or A5.5 as applicable.
- 3.2. Gas Metal-arc Process: Use electrode classification ER70S according to AWS A5.18.

4. QUALIFIED STATUS:

- 4.1. If the welder fails to <u>qualify</u> meet the <u>qualification requirements</u>, he <u>or she</u> may take a re-test provided <u>double the number of bars</u> two test specimens are welded for each <u>combination</u> specimen that failed. If <u>any of</u> the re-test <u>bars fail</u> specimens do not meet all requirements, the welder must wait 90 days before he <u>or she</u> can take the test again.
- 4.2. Qualified status shall be limited to two years from the date of completion of testing. If the welder is not engaged in the welding process for which he/she is qualified for a period exceeding 6 months, qualification status may be revoked within that two year period. Or, in the judgment of the Engineer, there is reason to question the welder's ability, qualification status may be revoked within that two year period.

5. COST OF TESTING:

- 5.1. The cost of the materials is the responsibility of the welder or fabricator.
- 5.2. The cost of testing weld specimens shall be the responsibility of the welder or fabricator. Contact the Physical Section in the Division of Materials to schedule testing and to obtain test cost information.

APPROVED	
	Director
	DIVISION OF MATERIALS
DATE	10/6/06

Attachment

Kentucky Method 64-109-0<u>56</u> Revised <u>10/6/06</u> Supersedes 64-109-05 Dated 1/05/05

km10906rev.doc

KENTUCKY TRANSPORTATION CABINET

Division of Materials

REMARKS:

TACK WELDERS

TC 64-752 Rev. 1/20/05 10/6/06

	Section 605.03.04			
ID NUMBER	Date Sampled			
INSPECTOR ID	INSPECTOR NAME			
COMPANY NAME	LOCATION			
TYPE OF INSPECTION				
MATERIAL CODE 7069				
INSPECTED QUANTITY		_UNITSEach		
Welder SSN	Expiration Da	nte		
Welder Name	Previously Approved for KY (Yes)(No)			
Route or Street				
City	State	_Zip Code		
PCN #Project	Number			
Date Received	Pass/Fail	Date Complete		
СНЕ	ECK APPROVED TACK V	VELDS		
3 <u>4</u> + 6T	6T4E + 5T			
Carbon Equivalent	Equivalent Carbon Equivalent			
6 + 3 <u>4</u> T	<u>4</u> T5E + 4T			
Carbon Equivalent	Carbon Equivalent			
WELDING PROCESS TYPE: Shield	ded Metal-Arc	Gas Metal-Arc		
Electrode or Wire Classification	Electrode Size	Preheat Temperature		
VISUAL INSPECTION: Appearance	e	Rod Oven Temp °F		
Undercut	Porosity			
Inspector Observing Welding				
Title		District		

COPIES: