

Kentucky Method 64-302-085
Revised ~~1/4/05~~02/22/08
Supersedes 64-302-053
Dated ~~2/12/03~~01/04/05

SLUMP OF PORTLAND CEMENT CONCRETE

Perform Test procedure according to ASTM C-143 with the following exceptions:

1. Obtain the sample in accordance with KM 64-301, Sampling Fresh Concrete.
2. Do not perform the slump test on concrete from a continuous mixer (concrete mobile) until 4 or 5 minutes after its discharge from the mixer.

APPROVED

DIRECTOR
DIVISION OF MATERIALS

DATE 02/22/08

~~APPROVED~~

~~_____
Director~~

~~_____
DIVISION OF MATERIALS~~

~~DATE 1/4/05~~

Kentucky Method 64-302-085
Revised ~~1/4/05~~02/22/08
Supersedes 64-302-053
Dated ~~2/12/03~~01/04/05

Km302085.doc