

Kentucky Method 64-301-08
Revised 02/22/08
Supersedes 64-301-03
Dated 02/17/03

SAMPLING FRESH CONCRETE

Obtain sample according to ASTM C-172 with the following exceptions:

1. Sample fresh concrete from delivery units in accordance with KM 64-113, Sampling Materials By Random Number Sampling
2. When concrete pumps or belt delivery systems are used, accomplish sampling simultaneously with placement at the discharge of the conveying equipment without stopping the flow of concrete to the area of work.
3. Do not perform the slump test on concrete from a continuous mixer (concrete mobile) until 4 or 5 minutes after its discharge from the mixer.

APPROVED

DIRECTOR
DIVISION OF MATERIALS

DATE

02/22/08

Kentucky Method 64-301-08
Revised 02/22/08
Supersedes 64-301-03
Dated 02/17/03

Km30108.doc