

Kentucky Method 64-302-08
Revised 02/22/08
Supersedes 64-302-05
Dated 01/04/05

SLUMP OF PORTLAND CEMENT CONCRETE

Perform Test procedure according to ASTM C-143 with the following exceptions:

1. Obtain the sample in accordance with KM 64-301, Sampling Fresh Concrete.
2. Do not perform the slump test on concrete from a continuous mixer (concrete mobile) until 4 or 5 minutes after its discharge from the mixer.

APPROVED

DIRECTOR
DIVISION OF MATERIALS

DATE

02/22/08

Kentucky Method 64-302-08
Revised 02/22/08
Supersedes 64-302-05
Dated 01/04/05

Km30208.doc