

## Special Note for Crushed Stone Base - Modified

This Special Note will apply where indicated on the plans or in the proposal. Section reference herein are to the Department's Standard Specifications for Road and Bridge Construction, current edition.

1.0 DESCRIPTION: Follow the Standard Specifications for Crushed Stone Base, sections 302 and 805, except the gradation and any payment reductions shall follow the table below. Contractor must remove and replace any material falling outside the reduction chart values.

GRADATION - CRUSHED STONE BASE - MODIFIED (1)							
Payment Reduction	Sieve Size-Percent passing						
	2 1/2 inch	1 1/2 inch	3/4 inch	3/8 inch	No. 4	No. 30	No. 200
0%	100	90-100	60-95	30-70	15-45	5-20	0-5
10%		88-99	58-59	28-29		3-4	
10%	98-99		96-97	71-72		21-22	
20%		86-87	56-57	26-27	14	1-2	
20%	96-97		98	73	46	23	
30%		84-85	54-55	24-25	13	0	
30%	95		99	74	47	24	
50%		83	53	23	12		
50%	94		100	75	48	25	6

(1) Gradation to be performed by wet sieve KM 64-620 or AASHTO T 11/T 27.

2.0 PAYMENT. The Department will pay for Crushed Stone Base - Modified as per the standard specifications for Crushed Stone Base, section 302, except the pay item will be as follow:

<u>Code</u>	<u>Pay Item</u>	<u>Pay Unit</u>
24965EC	CRUSHED STONE BASE - MODIFIED	TON