

**Special Note for**  
**Longitudinal Texturing of Concrete Pavement**

Provide concrete pavement with longitudinal texturing. Depth, spacing, and any other details in regards to texturing will be completed as per Specification 501.03.13 H) with the exception of the direction of texturing, and the spacing of longitudinal grooves. Spacing for the longitudinal grooves will be 3/4 inch. Obtain the Resident Engineer's approval as per the method of construction. A test area will not be necessary, but the Engineer does retain the authority to stop work if a problem occurs.

Diamond grinding will not be considered an acceptable alternative. Ride Quality will also not be waived.

No direct payment will be made for texturing of the pavement and it will be considered incidental to JPC Pavement.