

Kentucky Method 64-416-082  
Revised ~~12/13/01~~02/21/08  
Supersedes KM 64-416-0299  
Dated ~~10/99~~12/13/01

## PLASTIC SET TEST FOR ASPHALT MASTIC

1. SCOPE: This test method measures the toughness, shrinkage, adhesion, and cracking of asphalt mastic after curing.
2. APPARATUS -
  - 2.1. Provide a tinned panel, approximately 5 by 3 by 0.013 inches.
  - 2.2. Provide a spatula, capable of spreading the sample into a “smear” which is 1/16 to 1/8 of an inch thick.
3. SAMPLE: Ensure that the size of the test sample is ~~shall be~~  $3.0 \pm 0.5$  grams.
4. PROCEDURE -
  - 4.1. Apply the thin layer of the asphalt mastic, which is 1/16 to 1/8 of an inch thick and weighs approximately 3 g, to the tinned panel.
  - 4.2. Allow the specimen to cure at room temperature for 24 hours.
  - 4.3. Visually examine the specimen for the following:
    - 4.3.1. Toughness;
    - 4.3.2. Shrinkage;
    - 4.3.3. Adhesion to the tinned panel; and
    - 4.3.4. Cracking.

5. REPORT: Ensure that the asphalt mastic sets to a tough, plastic coating and does not shrink, crack, or loosen from the surface after the 24-hour cure period.

APPROVED

\_\_\_\_\_  
DIRECTOR  
DIVISION OF MATERIALS

DATE 02/21/08

APPROVED

\_\_\_\_\_  
Director

\_\_\_\_\_  
Division of Materials

DATE 12/13/01

Kentucky Method 64-416-0~~82~~

Revised ~~12/13/01~~ 02/21/08

Supersedes KM 64-416-~~9902~~

Dated 12/13/01

Km4160~~82~~.doc